

DOI: [10.29026/oea.2023.220008](https://doi.org/10.29026/oea.2023.220008)

Ostensibly perpetual optical data storage in glass with ultra-high stability and tailored photoluminescence

Zhuo Wang^{1†}, Bo Zhang^{1†}, Dezhi Tan^{2*} and Jianrong Qiu^{1,3*}

Long-term optical data storage (ODS) technology is essential to break the bottleneck of high energy consumption for information storage in the current era of big data. Here, ODS with an ultralong lifetime of 2×10^7 years is attained with single ultrafast laser pulse induced reduction of Eu^{3+} ions and tailoring of optical properties inside the Eu-doped aluminosilicate glasses. We demonstrate that the induced local modifications in the glass can stand against the temperature of up to 970 K and strong ultraviolet light irradiation with the power density of 100 kW/cm². Furthermore, the active ions of Eu^{2+} exhibit strong and broadband emission with the full width at half maximum reaching 190 nm, and the photoluminescence (PL) is flexibly tunable in the whole visible region by regulating the alkaline earth metal ions in the glasses. The developed technology and materials will be of great significance in photonic applications such as long-term ODS.

Keywords: ultrafast laser; photoluminescence tailoring; ultralong lifetime; optical data storage

Wang Z, Zhang B, Tan DZ, Qiu JR. Ostensibly perpetual optical data storage in glass with ultra-high stability and tailored photoluminescence. *Opto-Electron Adv* 6, 220008 (2023).

Introduction

In the development history of human society, data storage plays an indispensable and pivotal role, it has significantly boosted spacious domains from social science to industrial production. With the advent of the Internet of Things and artificial intelligence, the long lifetime and large capacity of information storage are increasingly high demand. Accordingly, optical data storage (ODS) technique provides a highly fascinating alternative to conventional storage techniques (semiconductor or magnetic-based storage) with lower energy consumption, larger capacity, higher efficiency, and longer lifetime¹⁻⁵. However, accounting for 80% of the total stored data

generated by the government, data disaster recovery centers, and archives are not frequently accessed but still need to be available over long periods in an easy access method. The typical lifetime of mature ODS is hundreds of years that is still far from meeting the requirements of next-generation information storage⁶⁻⁸. Although the ODS based on ultrafast laser induced volume periodic structures has an ultralong lifetime, multipulse irradiation with the pulse energy up to micro-joule is necessary for writing, which will slow down the writing speed and increase the power consumption⁹. Developing long-term stable ODS based on single pulse writing process can not only notably reduce the energy dissipation

¹State Key Laboratory of Modern Optical Instrumentation, and College of Optical Science and Engineering, Zhejiang University, Hangzhou 310027, China; ²Zhejiang Lab, Hangzhou 311100, China; ³CAS Center for Excellence in Ultra-intense Laser Science, Chinese Academy of Sciences, Shanghai 201800, China.

[†]These authors contributed equally to this work.

*Correspondence: DZ Tan, E-mail: wctdz@zju.edu.cn; JR Qiu, E-mail: qjr@zju.edu.cn

Received: 13 January 2022; Accepted: 26 March 2022; Published online: 31 August 2022



Open Access This article is licensed under a Creative Commons Attribution 4.0 International License.

To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2023. Published by Institute of Optics and Electronics, Chinese Academy of Sciences.

associated with frequent data migration but also increase the efficiency of data writing.

Tailoring of optical properties of active centers or dopants in solid matrix has extensively boosted the applications of glasses and crystals in optical communication, information storage, photonic device, and display^{2,10–13}. Typically, the spectroscopic features of the active centers or dopants are highly dependent on the local structures of amorphous glass or crystal field and generally tuned via chemical component modulation and homogeneous heat treatment of the matrix^{14–17}. Recently, ultrafast laser has also been established to be an effective tool for tailoring optical properties of transparent solids and hence implementing new functionalities with three-dimensional (3D) structuring capability^{18–23}. For example, modifying the local structures and valence of active ions in transparent matrix endows writing information in the local volume by distinct photoluminescence (PL) emission properties that enable large capacity ODS with a high signal-to-noise ratio^{24–27}. However, the PL is generally induced by multipulse laser irradiation, which limits the writing speed of ODS. Besides, an obvious decrease in the PL intensity of active ions is usually observable at high temperatures, which is detrimental for long-term device operation^{28–30}. Hence, the lifetime of ODS based on the distinct PL is limited to only a few hundred years or even several decades^{1,31}. It is a challenge to realize ODS that not only possesses a facile method and fast writing speed but also possesses an ultralong lifetime and excellent stability.

In this work, we report long-term and high writing speed ODS by tailoring the valence state of Eu^{3+} ions inside glass with single laser pulse. We demonstrate that the lifetime of stored information is as long as 2×10^7 years and the written local modifications can stand against the temperature of up to 970 K and intense ultraviolet irradiation (100 kW/cm^2). Furthermore, broadband emission of the active Eu^{2+} ions is observed with the full width at half maximum (FWHM) reaching 190 nm and the PL can be tuned in the whole visible region.

Results and discussion

Ordinarily, luminescent materials, a kind of widely employed ODS medium, are composed of a reasonable combination of certain active dopants with an inert matrix. Divalent europium cation (Eu^{2+}) is one of the extensively applied activators due to unequaled 4f-5d transition^{32–34}. The emission spectrum of Eu^{2+} is largely de-

pendent on the chemical compositions and structures of hosts as the 5d orbital is sensitive to the surrounding environment. Besides, aluminosilicate glass is considered as an outstanding category of host matrix due to the excellent stability and accessible synthesis method with relatively low cost of raw materials. Eu-doped earth-abundant aluminosilicate glass represents preeminent luminescence characteristics that can meet distinct optoelectronic applications. Therefore, Eu_2O_3 doped calcium-silicon-aluminum (Eu: CSA) glass is employed to serve as ODS matrix, among which intermediate elements including silicon and aluminum act as glass former, whereas the alkaline earth metal element (calcium) serves as glass modifier. Ultrafast laser is used to tailor PL properties of Eu: CSA glass to enable data writing. During laser-matter interaction, three-photon absorption occurs in the laser modified area, and active electrons and holes can be created in glass through multi-photon ionization process. When the electrons are trapped by Eu^{3+} , permanent photoreduction of Eu^{3+} will be achieved to generate Eu^{2+} , and different luminescence characters will be attained.

Figure 1(a) shows the PL spectra from Eu^{3+} in initial Eu: CSA glass before tailoring luminescence by femtosecond (fs) laser. A series of characteristic emission lines between 570 and 750 nm attributed to the ${}^5D_0 \rightarrow {}^7F_J (J = 0, 1, 2, 3, 4)$ transition appear^{8,35}. The target glass without doping (CSA glass) does not emit PL after ultrafast laser irradiation as illustrated in Fig. 1(b). Typical broadband PL of Eu^{2+} ions arises in Eu: CSA glass after tailoring luminescence with fs laser. The FWHM of the emission spectrum reaches 190 nm, which is much larger than that of the reported value of ~ 90 nm in the previous reports³⁰ (such as in the Eu-doped borate (Eu: BAN) glass (Fig. 1(c))). The anomalous spectra broadening can be attributed to the coexistence of Eu^{2+} ions and Eu^{3+} ions in glass (Fig. S4(a)). Besides, the random distribution of Si and Al will enhance the structural disorder and asymmetry thus leading to a broad spectral band. Furthermore, the PL can be stimulated both by 375 nm and 405 nm resulting from the big centroid shift as well as the energy level splitting. The Eu-doped glasses usually have less absorption after 400 nm, the PL of Eu^{2+} excited by 405 nm laser is barely detectable in borate glass as shown in Fig. 1(c). However, by tailoring the optical property of Eu: CSA glass, the absorption in ultraviolet region of Eu^{2+} doped glass becomes higher (Fig. 1(d)), and the PL emission can be excited by 405 nm laser, which provides a new choice of excitation for data




Fig. 1 | (a) PL spectra of initial Eu: CSA glass. (b) PL spectra of Eu: CSA and CSA glasses after irradiation. (c) PL spectra of Eu: BAN glass after ultrafast laser irradiation. The inset is the enlarged PL spectrum excited by 405 nm laser. (d) Absorption spectra of Eu: CSA and Eu: BAN glasses. Inset is an enlargement of absorbance from 350 to 430 nm.

reading. Besides, the bandgap of Eu: CSA glass is approximately 3.65 eV according to Fig. 1(d), indicating three-photon absorption during laser-matter interaction. Consequently, reduction of Eu^{3+} and tailoring of optical properties inside glass are achieved simultaneously and allow for tuning the PL of the active ions. The distinct PL in Eu: CSA glass resulting from Eu^{3+} and Eu^{2+} exhibits the possibility to serve as an ODS medium. Besides, potential multi-application of rare earth ions-doped glasses has been proposed, and ODS technology is one of the most important demonstrations.

To further demonstrate the performance of ODS in the devised glass, we systematically investigated the impact of used laser parameters including duration, pulse energy, repetition rate, and pulse number. As illustrated in Fig. 2(a), groups of dots are directly written into Eu: CSA glass by single pulse fs laser with controlled pulse

durations and pulse energies. Reading out of dot-array is exhibited in Fig. 2(b) and the result indicates even single pulse can induce local material modifications with PL strong enough to be used for data storage. Figure 2(c) shows that the diameter of the written dots increases with the increase in the pulse energy. The size of written dots can be reduced to 600 nm when the pulse energy is reduced to 96 nJ (Fig. S5(b)), and the density of ODS is approximately 1.4 Tbit cm^{-3} . Figure 2(d) demonstrates the PL intensity of dots written with different pulse energies and pulse durations. The PL intensity increases with the increment in the writing pulse energy. A decrease in pulse duration leads to an increase in the PL intensity of Eu^{2+} and a decrease in the pulse energy threshold for writing emissive dots. Figure 2(e) demonstrates the PL intensity as a function of repetition rate and pulse number, which indicates the presence of a broad grayscale of




Fig. 2 | (a) Optical image of recorded information in the glass. (b) Reading out of information by PL mapping. Scale bar: 10 μm . (c) Relationship between emissive dot size and pulse energy. (d) PL intensity of dots written with diverse pulse durations and pulse energies. (e) PL intensity of dots written with various repetition rates and pulse numbers. (f) 16 levels of grayscale assignment based on the relation between PL intensity and pulse number.

PL intensity that can serve as another degree of freedom in ODS. Figure 2(f) demonstrates up to 16 levels of grayscale and in this case each written dot can be coded in a 4-bit-format (from 0000 to 1111), which allows further expansion of storage capacity. Dots in a 4-bit format can also be achieved by controlling pulse energy, as shown in Fig. S6. It is worth to note the diameter of writing dots increases with the increase of pulse number and pulse energy. Too small or large bit spacing will lead to a decrease in bit contrast or storage density, as a result, appropriate bit spacing is very crucial to keep the balance between low cross-talk and high storage capacity.

As demonstrated in Fig. 3(a–c), Chinese characters of “zhe jiang da xue” are translated into a binary symbol and recorded in various layers of the transparent Eu:CSA glass. The dots in layer 1 and layer 2 are written by single pulse of fs laser with pulse energy of 200 nJ, and dots in layer 3 and layer 4 are written by 250 nJ and 300 nJ fs laser, respectively. The first layer of dots is written at the depth of 50 μm , and the spacing between adjacent layers in the z -direction is 10 μm . Reading out of the recorded information can be achieved by collecting the PL from the dots without and with fs laser writing, which corresponds to the “0” and “1” states in the binary system, respectively. No signal crosstalk is observed between different adjoining layers by controlling the

writing pulse number and pulse energy (Fig. 3(b)) and it is also essential for 3D ODS. As the information writing is realized by single pulse incidence, the amount of data written per unit time can be considerably large, which is determined by the laser repetition rate and scanning speed of the stage. Therefore, high repetition frequency in the megahertz range is more favorable for improving information storage efficiency. Besides, a complicated logo pattern is also successfully recorded in glass by selectively tailoring the luminescence with continuous line scanning with 0.5 μJ pulse energy fs laser and the scanning speed is 80 $\mu\text{m}/\text{s}$. The recorded pattern can be read by 405 nm laser stimulation as demonstrated in Fig. 3(d) and it can also be stored in different layers. The non-uniformity of PL intensity, such as the low PL intensity in the bottom right, is due to the non-uniformity of glass thickness, which can be optimized by better polishing. The successful demonstration of 3D information recording and reading demonstrates the feasibility of ODS technology in the Eu_2O_3 doped aluminosilicate glass.

A long-term ODS technology with lifetime longer than a few hundred years can not only significantly reduce the energy dissipation associated with frequent data migration but also increase the savings in expenditures, including electricity and costs of storage devices. Consequently, it is necessary to examine the lifetime of




Fig. 3 | Optical information writing and readout. (a) Schematic diagram of 3D information writing in the glass. (b) Recorded information in glass in different layers. Dots in layer 1 and layer 2 are written by single pulse with 200 nJ. Dots in layer 3 and layer 4 are written by single pulse with 250 nJ and 300 nJ, respectively. Scale bar: 10 μm . (c) Encode information by binary format. (d) Complicated logo pattern recorded in the glass. Scale bar: 20 μm .

recorded information in the devised material. As illustrated in Fig. 4(a), the stored information in Eu: CSA glass can survive under the temperature of up to 970 K. According to Arrhenius law (Eq. S7), the lifetime (Fig. 4(b)) of the PL signal that can sustain the stability and readability of recorded information is evaluated up to 2×10^7 years which is several orders of magnitude higher than current PL-based ODS approaches (Fig. 4(c))^{6,8}. The temperature tolerance of other Eu_2O_3 doped aluminosilicate glasses (Eu: DSA, D represents MgO, CaO, SrO, BaO) is demonstrated in Fig. 4(d), after two-hours heating at 770 K, the PL intensity decreased by only 17%, indicating a generally excellent storage lifetime in similar glass systems. This is because that in Eu: DSA glass, the tetrahedral symmetry around Eu^{2+} will decrease with the incorporation of Al^{3+} and Si^{4+} sites, and the energy level splitting of 5d band increases. Consequently, the activation energy for thermal quenching becomes higher, resulting in a more stable PL. Notably, the recorded information in Eu: CSA glass can withstand highly intense ultraviolet irradiation ($\sim 100 \text{ kW/cm}^2$) and be accurately read with an excitation power as low as 6 nW (corresponding to 2 W/cm^2 in Fig. 4(e)). The decay rate of PL intensity is reduced significantly in Eu: CSA glass as compared with the tolerability of ultraviolet irradiation in Ag-doped silicate (Ag: CSA) glass and Eu: BAN glass (Fig. 4(f)). These results firmly confirm the great potential of the Eu: CSA glass-mediated ODS in highly robust

long-term information storage.

In addition, the tailoring of luminescence can be universally attained in more glasses, such as employing other alkaline earth metal ions (including Mg, Sr, and Ba) to serve as glass modifiers. Similar broadband PL emitting by Eu^{2+} and several characteristic sharp PL peaks emitting by Eu^{3+} are collected, as shown in Fig. 5(a) and 5(b). It is worth noting that the emission of Eu^{2+} depends on surrounding environment. Hence by regulating the alkaline earth metal ions in aluminosilicate glasses, the PL emitted by Eu^{2+} ions can be tailored and it is flexibly tunable among the whole visible region. The Commission International de L'Eclairage (CIE) chromaticity coordinates of PL spectra in these aluminosilicate glasses changed gradually from (0.29, 0.35) to (0.43, 0.42) with an increase in the ratio of alkaline earth metal ion (Fig. 5(c)). As shown in Fig. 5(d), the energy gap between the 4f ground state and the lowest 5d excited level ($E_{fd}(\text{free})$) is approximately 4.216 eV (equal to 34000 cm^{-1}) for the free Eu^{2+} ion^{36,37}. However, the actual 4f–5d energy position ($E_{fd}(A)$) is generally smaller than that of the free 4f–5d energy gap when Eu^{2+} ions are doped into the host due to the influence of the surrounding environment on the 5d energy level. Generally, the emission of europium doped luminescence materials is determined by the spectroscopic redshift of the 5d energy position compared with that of free Eu^{2+} ion $D(A)$ consisting of the centroid shift (ϵ_c) and the energy level splitting $\epsilon_s(A)$ ³⁷. The




Fig. 4 | Stability of recorded information. (a) Thermal stability of PL in Eu: CSA glass. (b) Arrhenius plot of the decay rate. Grey area: error estimates. (c) Comparison of lifetime in ODS based on different media^{6,8}. (d) Comparison of thermostability of PL in Eu: DSA glasses. (e) PL stability of written dots under various excitation power densities. (f) PL stability of different ODS media.




Fig. 5 | (a) PL spectra of dots written in the aluminosilicate glasses by fs laser. (b) PL spectra of initial glasses. Excitation wavelength: 375 nm. (c) Optical emission of Eu²⁺ in CIE coordinates. (d) Schematic diagram of the real 5d energy position in an inorganic solid. (e) Spectroscopic red-shift in Eu: DSA glass.

emission spectrum is influenced by the lowest 5d energy level and Stokes shift (ΔS (Å)). The Stokes shift is related to equilibrium position offset and phonon energy. In Eu: DSA glasses, a larger cation ratio results in a bigger spectroscopic redshift, which originates from the synergistic contribution of a large centroid shift, energy level splitting and Stokes shift as illustrated in Fig. 5(e). Typically, when the radius of alkaline earth metal ions increases, the spectral polarizability of the closest anion neighbors increases, the typical coordination number of cations also exhibits an increasing trend, and the distance between Eu^{2+} and O^{2-} also decreases, hence leading to a bigger centroid shift. Thus, the luminescence properties of dopants in solid matrix can be manipulated in a wide range, which can greatly expand the potential applications of aluminosilicate glasses in storage, imaging, and display.

Conclusions

Here, a stable ODS technique with an ultralong lifetime of 2×10^7 years is proposed by ultrafast laser selectively regulating the valence state of doped active ions and tailoring optical properties of Eu^{2+} ions inside the Eu-doped aluminosilicate glasses. It is demonstrated that the stored information exhibits excellent tolerability to temperature (970 K) and ultraviolet irradiation (100 kW/cm^2). Furthermore, the active Eu^{2+} ions emit a broadband PL with FWHM of 190 nm, and the PL can be flexibly tuned in the entire visible range by adjusting the modifiers in glasses. The proposed ODS technique with ultralong lifetime is of great significance for breaking the bottleneck of large energy consumption in practical applications.

References

- Zhu LW, Cao YY, Chen QQ, Quyang X, Xu Y et al. Near-perfect fidelity polarization-encoded multilayer optical data storage based on aligned gold nanorods. *Opto-Electron Adv* 4, 210002 (2021).
- Zhang B, Wang Z, Tan DZ, Liu XF, Xu BB et al. Ultrafast laser inducing continuous periodic crystallization in the glass activated via laser-prepared crystallite-seeds. *Adv Opt Mater* 9, 2001962 (2021).
- Zhang QM, Xia ZL, Cheng YB, Gu M. High-capacity optical long data memory based on enhanced Young's modulus in nanoplasmonic hybrid glass composites. *Nat Commun* 9, 1183 (2018).
- Chen WL, Yan Z, Tian J, Liu SY, Gao JC et al. Flexible four-dimensional optical data storage enabled by single-pulse femtosecond laser irradiation in thermoplastic polyurethane. *Opt Lett* 46, 3211–3214 (2021).
- Yu JB, Luo MT, Lv ZY, Huang SM, Hsu HH et al. Recent advances in optical and optoelectronic data storage based on luminescent nanomaterials. *Nanoscale* 12, 23391–23423 (2020).
- Gao L, Zhang QM, Evans RA, Gu M. 4D Ultra-high-density long data storage supported by a solid-state optically active polymeric material with high thermal stability. *Adv Opt Mater* 9, 2100487 (2021).
- Yang ZT, Du JR, Martin LIDJ, Feng A, Cosaert E et al. Designing photochromic materials with large luminescence modulation and strong photochromic efficiency for dual-mode rewritable optical storage. *Adv Opt Mater* 9, 2100669 (2021).
- Wang Z, Zhang B, Tan DZ, Qiu JR. Long-term optical information storage in glass with ultraviolet-light-preprocessing-induced enhancement of the signal-to-noise ratio. *Opt Lett* 46, 3937–3940 (2021).
- Zhang JY, Gecevicius M, Beresna M, Kazansky PG. Seemingly unlimited lifetime data storage in nanostructured glass. *Phys Rev Lett* 112, 033901 (2014).
- Liao HX, Zhao M, Zhou YY, Molokeev MS, Liu QL et al. Polyhedron transformation toward stable narrow-band green phosphors for wide-color-gamut liquid crystal display. *Adv Funct Mater* 29, 1901988 (2019).
- Sun K, Tan DZ, Fang XY, Xia XT, Lin DJ et al. Three-dimensional direct lithography of stable perovskite nanocrystals in glass. *Science* 375, 307–310 (2022).
- Fernandez TT, Gross S, Privat K, Johnston B, Withford M. Designer glasses—future of photonic device platforms. *Adv Funct Mater* 32, 2103103 (2022).
- Xia TF, Cao WQ, Cui YJ, Yang Y, Qian GD. Water-sensitive multicolor luminescence in lanthanide-organic framework for anti-counterfeiting. *Opto-Electron Adv* 4, 200063 (2021).
- Yang ZT, Du JR, Martin LIDJ, van der Heggen D, Poelman D. Highly responsive photochromic ceramics for high-contrast rewritable information displays. *Laser Photonics Rev* 15, 2000525 (2021).
- Du JR, Feng A, Poelman D. Temperature dependency of trap-controlled persistent luminescence. *Laser Photonics Rev* 14, 2000060 (2020).
- Yang ZY, Zhou YY, Qiao JW, Molokeev MS, Xia ZG. Rapid synthesis of red-emitting $\text{Sr}_2\text{Sc}_{0.5}\text{Ga}_{1.5}\text{O}_5$: Eu^{2+} phosphors and the tunable photoluminescence via Sr/Ba substitution. *Adv Opt Mater* 9, 2100131 (2021).
- Hu T, Ning LX, Gao Y, Qiao JW, Song EH et al. Glass crystallization making red phosphor for high-power warm white lighting. *Light Sci Appl* 10, 56 (2021).
- Zhang B, Tan DZ, Liu XF, Tong LM, Kazansky PG et al. Self-organized periodic crystallization in unconventional glass created by an ultrafast laser for optical attenuation in the broadband near-infrared region. *Adv Opt Mater* 7, 1900593 (2019).
- Lei YH, Sakakura M, Wang L, Yu YH, Wang HJ et al. High speed ultrafast laser anisotropic nanostructuring by energy deposition control via near-field enhancement. *Optica* 8, 1365–1371 (2021).
- Tan DZ, Wang Z, Xu BB, Qiu JR. Photonic circuits written by femtosecond laser in glass: improved fabrication and recent progress in photonic devices. *Adv Photonics* 3, 024002 (2021).
- Zhang B, Wang L, Chen F. Recent advances in femtosecond laser processing of LiNbO_3 crystals for photonic applications. *Laser Photonics Rev* 14, 1900407 (2020).
- Zhang S, Xu LS, Wu J, Yang Y, Zhang CX et al. Femtosecond laser micro-nano processing for boosting bubble releasing of

- gas evolution reactions. *Nano Res* **15**, 1672–1679 (2022).
23. Zhang B, Tan DZ, Wang Z, Liu XF, Xu BB et al. Self-organized phase-transition lithography for all-inorganic photonic textures. *Light Sci Appl* **10**, 93 (2021).
 24. Gu M, Zhang QM, Lamon S. Nanomaterials for optical data storage. *Nat Rev Mater* **1**, 16070 (2016).
 25. Kallepalli DLN, Alshehri AM, Marquez DT, Andrzejewski L, Scaino JC et al. Ultra-high density optical data storage in common transparent plastics. *Sci Rep* **6**, 26163 (2016).
 26. Montelongo Y, Yetisen AK, Butt H, Yun SH. Reconfigurable optical assembly of nanostructures. *Nat Commun* **7**, 12002 (2016).
 27. Wang Z, Tan DZ, Qiu JR. Single-shot photon recording for three-dimensional memory with prospects of high capacity. *Opt Lett* **45**, 6274–6277 (2020).
 28. Kim YH, Arunkumar P, Kim BY, Unithrattil S, Kim E et al. A zero-thermal-quenching phosphor. *Nat Mater* **16**, 543–550 (2017).
 29. Royon A, Bourhis K, Bellec M, Papon G, Bousquet B et al. Silver clusters embedded in glass as a perennial high capacity optical recording medium. *Adv Mater* **22**, 5282–5286 (2010).
 30. Wang L, Xie RJ, Li YQ, Wang XJ, Ma CG et al. $\text{Ca}_{1-x}\text{Li}_x\text{Al}_{1-x}\text{Si}_{1+x}\text{N}_3$: Eu^{2+} solid solutions as broadband, color-tunable and thermally robust red phosphors for superior color rendition white light-emitting diodes. *Light Sci Appl* **5**, e16155 (2016).
 31. Gu M, Li XP, Cao YY. Optical storage arrays: a perspective for future big data storage. *Light Sci Appl* **3**, e177 (2014).
 32. Dai PP, Li C, Zhang XT, Xu J, Chen X et al. A single Eu^{2+} -activated high-color-rendering oxychloride white-light phosphor for white-light-emitting diodes. *Light Sci Appl* **5**, e16024 (2016).
 33. Qiao JW, Zhou GJ, Zhou YY, Zhang QY, Xia ZG. Divalent europium-doped near-infrared-emitting phosphor for light-emitting diodes. *Nat Commun* **10**, 5267 (2019).
 34. Joos JJ, van der Heggen D, Martin LIDJ, Amidani L, Smet PF et al. Broadband infrared LEDs based on europium-to-terbium charge transfer luminescence. *Nat Commun* **11**, 3647 (2020).
 35. Wang C, Peng MY, Jiang N, Jiang XW, Zhao CJ et al. Tuning the Eu luminescence in glass materials synthesized in air by adjusting glass compositions. *Mater Lett* **61**, 3608–3611 (2007).
 36. Dorenbos P. Relation between Eu^{2+} and Ce^{3+} f \leftrightarrow d-transition energies in inorganic compounds. *J Phys Condens Matter* **15**, 4797–4807 (2003).
 37. Zhao M, Zhang QY, Xia ZG. Structural engineering of Eu^{2+} -doped silicates phosphors for led applications. *Acc Mater Res* **1**, 137–145 (2020).

Acknowledgements

We are grateful for financial supports from the National Key R&D Program of China (No. 2021YFB2802000 and 2021YFB2800500); the National Natural Science Foundation of China (Grant Nos. U20A20211, 51902286, 61775192, 61905215, and 62005164); Key Research Project of Zhejiang Lab; the State Key Laboratory of High Field Laser Physics (Shanghai Institute of Optics and Fine Mechanics, Chinese Academy of Sciences), and China Postdoctoral Science Foundation (2021M702799).

Author contributions

The manuscript was written through contributions of all authors. All authors have given approval to the manuscript.

Competing interests

The authors declare no competing financial interests.

Supplementary information

Supporting information is available for this paper at <https://doi.org/10.29026/oea.2023.220008>